

Received:06/28/2019 Completed:08/02/2019 Letter: N JR P.O.#: Test Report #: 3-33244-0-

Client's Identification Lot No.: 001. Treated. Date of Mfg.: 05/21/2019. Composition: ██████████. Weight: 2,20 lbs.
 Product End Use: 12/31/2019.

Tested For: **Camille E, Ferber** Key Test: NFPA 701-2019 TM#1 275
 Ferber Group LLC
 16192 Coastal Hwy Tel: 1-(864)-778-8888 Ext:
 Lewes, DE 19958 Fax: 1-()- -

REMARKS:

- Flames did not project above the top of the specimen.
- Flames projected above the top of the specimen; Specimen #'s _____
- Other: Partical board cut to 15" x 6" x 0.403" submitted by client for TM#1.

FAILURE CRITERIA: As cited by NFPA 701 - 2019 Edition Test Method #1


Afterflame	Flaming Drip/Debris (Mean)	Weight Loss (percent)	
		Mean	Individual Specimen
*	Exceeds 2 seconds	Exceeds 40%	Exceeds Mean + 3 SD

CONCLUSION: Based on the Results on page 1 and the above Failure Criteria cited by NFPA 701 - 2019 Edition Test Method #1, the item tested:

Passes; Fails; Requires testing of 10 additional specimens
 i.e. only one individual specimen failure was noted

* Afterflame is required to be recorded; however, the NFPA document does not factor it into the Failure Criteria reporting requirements. It should be noted that excessive afterflames could be cause for rejection by local fire authorities performing "match" field tests.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



 AUTHORIZED SIGNATURE
 SGS GOVMARK
 /jab /gb

AUG 06 2019